



Berg Steel Pipe Corp.
a Company of the Europipe Group

Helpful Tables

		lb/ft matrix															
		Outside diameter															
		24	26	28	30	32	34	36	40	42	48	50	52	54	56	60	64
Wall Thickness	0.250	63.47	68.82	74.16	79.51	84.85	90.20	95.54	106.23	111.58	127.61	132.96	138.30	143.65	148.99	159.68	170.37
	0.281	71.25	77.26	83.26	89.27	95.28	101.29	107.30	119.31	125.32	143.34	149.35	155.36	161.37	167.37	179.39	191.40
	0.312	79.01	85.68	92.35	99.02	105.69	112.36	119.03	132.37	139.04	159.05	165.72	172.39	179.06	185.74	199.08	212.42
	0.344	86.99	94.35	101.70	109.06	116.41	123.77	131.12	145.83	153.18	175.25	182.60	189.96	197.31	204.67	219.38	234.09
	0.375	94.71	102.72	110.74	118.76	126.78	134.79	142.81	158.85	166.86	190.92	198.93	206.95	214.97	222.99	239.02	255.06
	0.406	102.40	111.08	119.76	128.44	137.12	145.80	154.48	171.84	180.52	206.56	215.24	223.93	232.61	241.29	258.65	276.01
	0.438	110.32	119.69	129.05	138.42	147.78	157.14	166.51	185.24	194.60	222.70	232.06	241.42	250.79	260.15	278.88	297.61
	0.469	117.98	128.00	138.03	148.06	158.08	168.11	178.14	198.19	208.22	238.30	248.33	258.36	268.38	278.41	298.47	318.52
	0.500	125.61	136.30	146.99	157.68	168.37	179.06	189.75	211.13	221.82	253.89	264.58	275.27	285.96	296.65	318.03	339.41
	0.562	140.81	152.83	164.84	176.86	188.87	200.89	212.90	236.93	248.95	285.00	297.01	309.03	321.04	333.06	357.09	381.12
	0.625	156.17	169.54	182.90	196.26	209.62	222.99	236.35	263.07	276.44	316.52	329.89	343.25	356.61	369.97	396.70	423.42
	0.688	171.45	186.16	200.87	215.58	230.29	245.00	259.71	289.13	303.84	347.97	362.68	377.39	392.09	406.80	436.22	465.64
	0.750	186.41	202.44	218.48	234.51	250.55	266.58	282.62	314.69	330.72	378.83	394.86	410.90	426.93	442.97	475.04	507.11
	0.812	201.28	218.64	236.00	253.36	270.72	288.08	305.44	340.16	357.52	409.61	426.97	444.33	461.69	479.05	513.77	548.49
	0.875	216.31	235.01	253.72	272.43	291.14	309.84	328.55	365.97	384.67	440.80	459.50	478.21	496.92	515.63	553.04	590.46
	0.938	231.25	251.30	271.36	291.41	311.47	331.52	351.57	391.68	411.74	471.90	491.96	512.01	532.06	552.12	592.23	632.34
	1.000	245.87	267.25	288.63	310.01	331.39	352.77	374.15	416.91	438.29	502.43	523.81	545.19	566.57	587.95	630.71	673.47
1.125	275.10	299.15	323.21	347.26	371.31	395.36	419.42	467.52	491.57	563.73	587.78	611.84	635.89	659.94	708.05	756.15	
1.250	304.00	330.72	357.45	384.17	410.90	437.62	464.35	517.80	544.52	624.70	651.42	678.15	704.87	731.60	785.05	838.50	
1.375	332.56	361.96	391.35	420.75	450.15	479.55	508.94	567.74	597.14	685.33	714.73	744.12	773.52	802.92	861.71	920.51	
1.500	360.79	392.86	424.93	457.00	489.07	521.14	553.21	617.35	649.42	745.63	777.70	809.77	841.84	873.91	938.05	1002.19	

Formula based on API 5L 42nd edition July 2000